



MYK LATICRETE

LATICRETE® 1776 Grout Admix Plus



Polymer Grout Admix designed for use with LATICRETE® 500/600 Series Grout, in place of water to provide a dense, colour fast grout joint that inhibits stain causing bacteria, mold and mildew growth with Microban®.

Features / Benefits

Makes the cement grouts:

- Weather resistant
- Colour fast
- Easy application and clean up.
- Easy maintenance
- Non-cracking & Non-shrink
- Water and shock resistant.
- Improves flexibility and durability of grout

Application

Used in place of water, LATICRETE® 1776 Grout Admix Plus improves the performance of Portland cement grouts. Designed for interior and exterior floor and wall joints of all types of ceramic tile, vitreous, semi-vitreous tile, glass mosaic tiles, terrazzo, brick, marble, natural stone and agglomerate stone installation.

Substrates

- Ceramic tile
- Vitrified tile
- Glass Mosaic Tiles
- Granite
- Marble
- Agglomerates (Engineered Stones)
- Precast Terrazzo tiles
- Bricks

Compliance

Member of
Indian Green Building Council



Approved American National Standards



TECHNICAL DATA

Applicable Standards:

Laticrete 600 Series un-sanded grout, when mixed with Laticrete 1776 grout admix:

ANSI A118.6; ISO 13007 – 4(CG1) / EN 13888

ANSI Data		
Property / Test Method	Requirement	Typical Values
Linear Shrinkage after 27 days: ANSI A118.6: Clause 4.3	Max 0.30%	0.19% - 0.23%
Water Absorption after 27 days: ANSI A118.6: Clause 4.4	Max 18%	10% - 13%
Compressive Strength after 1 day: ANSI A118.6: Clause 4.5	Min 500 psi (3.43 Mpa)	570 – 900 psi (3.91 – 6.18 Mpa)
Compressive Strength after 28 days: ANSI A118.6: Clause 4.5	Min 3000 psi (20.62 Mpa)	3100 – 3200 psi (21.31 – 22.00 Mpa)
Tensile Strength after 28 days: ANSI A118.6: Clause 4.6	Min 250 psi (1.71 Mpa)	350 – 400 psi (2.40 – 2.75 Mpa)
Flexural Strength after 28 days: ANSI A118.6: Clause 4.7	Min 500 psi (3.43 Mpa)	600 – 800 psi (4.12 – 5.50 Mpa)

The grout mortar conforms to ANSI A 118.6

ISO / EN Data		
Property / Test Method	Requirement	Typical Values
Abrasion resistance: ISO 13007 – 4: Clause 4.4; EN 12808 - 2	$\leq 2000 \text{ mm}^3$	1000 – 1500 mm^3
Flexural strength under standard conditions: ISO 13007 – 4: Clause 4.1.3; EN 12808 - 3	$\geq 2.5 \text{ N / mm}^2$	4.0 – 5.5 N / mm^2
Flexural strength under freeze and thaw cycles: ISO 13007 – 4: Clause 4.1.5; EN	$\geq 2.5 \text{ N / mm}^2$	3.5 – 5.0 N / mm^2

12808 – 3		
Compressive Strength under standard conditions: ISO 13007 – 4: Clause 4.1.4; EN 12808 – 4	$\geq 15 \text{ N / mm}^2$	21 – 22 N / mm^2
Compressive Strength under freeze & thaw cycles: ISO 13007 – 4: Clause 4.1.5; EN 12808 – 4	$\geq 15 \text{ N / mm}^2$	20 – 22 N / mm^2
Shrinkage: ISO 13007 – 4: Clause 4.3 : EN 12808 – 4	$< 3 \text{ mm / m}$	1.9 – 2.3 mm / m
Water Absorption after 30 Minutes: ISO 13007 – 4: Clause 4.2; EN 12808 – 5	$\leq 5.0 \text{ g}$	2.0 – 2.5 g
Water Absorption after 240 Minutes: ISO 13007 – 4: Clause 4.2; EN 12808 – 5	$\leq 10 \text{ g}$	4.0 – 6.0 g

The grout mortar conforms to ISO 13007 – 4 (CG1) / EN 13888.

Packaging:

20 ltr Pail
 5 ltr – (4x5ltr) – Carton
 400ml – (10x400ml) – Carton
 200ml – (20x200ml) – Carton

Colour:

Milky white

Coverage:

- a) 375 ml to 400 ml per Kg of Un-sanded Grouts like Laticrete® 600 Series grout
- b) 175 ml to 200 ml per Kg of Sanded grouts like Laticrete® 500 Series grout.

Working Properties at 70° F (21° C)

LATICRETE® 1776 Grout Admix Plus mixed with LATICRETE® 600 series un-sanded Grout

Pot Life	1 hour
Time to Foot Traffic	24 hours
Time to Heavy Traffic	72 hours
Wet Density	1730 kg/m^3

INSTALLATION

Surface Preparation:

Before grouting, remove spacers and debris in grout joints and remove dust and dirt using a wet sponge. Do not leave water standing in joints. Substrate temperature must be between 40°F (4°C) and 90°F (32°C). Apply grout release or sealer if necessary.

Mixing:

Stir or shake LATICRETE® 1776 Grout Admix Plus thoroughly before use.

Add LATICRETE® Sanded Grout (500 Series) or LATICRETE® Unsanded Grout (600 Series) powder to proper amount of LATICRETE® 1776 Grout Admix Plus and mix by hand or with a slow speed mixer (<300 RPM) to a smooth, stiff consistency. Dampen tile surface with water. Spread with a sharp, firm rubber grout float. Work the grout into the joints until completely filled. Use diagonal strokes to pack the joints. Insure that joint is filled and grout is not just sitting on top (i.e. "bridging the joint").

Note: For fuller flush joints sprinkle a thin layer of dry grout powder over surface immediately after grouting. When grout darkens over joint, buff with burlap, carpet remnant or cotton rag to pack joint and clean face of tile.

Cleaning:

Grout Primary Cleaning - Remove excess grout from the face of the tiles with the edge of the grout float. Hold the float at a 90° angle and pull it at a 45° angle diagonally across the joints and tile to avoid pulling out the material.

Grout Secondary Cleaning - Remove remaining grout with a damp sponge (not wet) or a damp towel. Work diagonally to the joints. Allow to dry. When the grout joints are firm polish the surface with a coarse nylon pad or coarse cloth and minimal water.

Important site Checks: Notes to the specifiers:

- It is recommended to check the colour of the grout, if it is meeting the desired colour of the client
- It is recommended to do a small area with actual tile/stone at site and check for any colour ingress into the tile/stone. Many tiles / stones have high absorption which may lead to wet patches / discoloration / colour marks.
- Plan to provide proper movement joints, peripheral joints as per TCA, EJ 171 detail to accommodate movements in tile/stone and use flexible grout / sealant to fill these movement joints.

Note: Use caution when polishing soft glazed tiles or polished stone.

* Contact MYK LATICRETE technical services for large format tile or stone installations on exterior surfaces.

Shelf Life:

Factory sealed packs of this product are guaranteed to be of first quality for two (2) years* if stored off the ground in a dry area.

*High humidity will reduce the shelf life of bagged product.

Limitations

- Consult with Technical Services for specific exterior grouting recommendations.
- For industrial applications exposed to high concentrations of food and mineral acids and to high heat, use LATAPOXY®2000 Industrial Epoxy Grout.
- Protect from exposure to acids and strong cleaners during service periods. Acidic cleaners can neutralize the cement based grouts which leads to change of colour, cracking and powdering
- Adhesives/mastics, mortars and grouts for ceramic tile, pavers, brick and stone are not replacements for waterproof membranes. When a waterproof membrane is required, use LATICRETE® **Hydro ban** / 9237 Waterproof Membrane.

MAINTENANCE:

LATICRETE® and LATAPOXY® grouts require routine cleaning with neutral pH soap and water or MYK LATICRETE Clenza series suitable cleaners. All other LATICRETE® and LATAPOXY® materials require no maintenance but proper installation as per instruction.

Performance and durability may depend on properly maintaining of Installed area.

Customer Care

MYK LATICRETE India Pvt Ltd.

Plot No. 30/C (Sy. No. 83/1), Orbit Building,
17th Floor, Tower 1, Knowledge City, TSIC,
Raidurg, Ranga Reddy Dist.,
Hyderabad - 500 081, Telangana, INDIA.
Tel: +91-40-68173100
e-mail: cc@myklaticrete.com
Website: www.myklaticrete.com